



**In the Claims**

1. (Withdrawn and currently amended) A block copolymer comprising a fluorinated block and at least one non-fluorinated block, wherein the fluorinated block has the following structure:



wherein the non-fluorinated block has the following structure:



wherein R<sub>1</sub> is selected from the group consisting of -CH<sub>3</sub>, -CF<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -phenyl, naphthyl, -COOR<sub>3</sub>, and -CONR<sub>3</sub>R<sub>4</sub>;


wherein R<sub>2</sub> is selected from the group consisting of -H, -CH<sub>3</sub>, -CF<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -phenyl, and naphthalenyl; and

wherein R<sub>3</sub> and R<sub>4</sub> are selected from the group consisting of -CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>OH, and -PEG<sub>1</sub>;

wherein n is a positive integer; and

wherein m is a positive integer.

2. (Withdrawn and currently amended) The block copolymer of claim 1 having a formula of the following structure:



wherein  $R_1$  is selected from the group consisting of  $-CH_3$ ,  $-CH_2CH_3$ ,  $-CH_2CH_2CH_3$ ,  $-CH_2CH_2CH_2CH_3$ ,  $-CH_2CH_2OH$ , and  $-PEG$ , and

wherein  $R_2$  is selected from the group consisting of  $-H$  or  $-CH_3$ ,  $-CF_3$ ,  $-CH_2CH_3$ ,  $-CH_2CH_2CH_3$ ,  $-CH_2CH_2CH_2CH_3$ ,  $-phenyl$  and  $naphthyl$ ,


wherein  $n$  is a positive integer; and

wherein  $m$  is a positive integer.

3. (Withdrawn) The block copolymer of claim 2 wherein  $R_1$  is  $-CH_3$ ,  $-CH_2CH_3$ ,  $-CH_2CH_2CH_3$ ,  $-CH_2CH_2CH_2CH_3$ ,  $-CH_2CH_2OH$ , or  $-PEG$ , and

wherein  $R_2$  is  $-H$  or  $-CH_3$ .


4. (Withdrawn and currently amended) A block copolymer comprising a fluorinated block and at least one non-fluorinated block, wherein the fluorinated block has the following structure:




wherein the non-fluorinated block is a polymer selected from the group consisting of polyesters, polyethers, polyanhydrides, polyglycols, poly(alkylene oxides), polyhydroxyalkanoates, polyphosphazenes, polyurethanes, and a combination thereof; and

wherein n is a positive integer.

5. (Withdrawn and currently amended) A polymeric coating composition comprising a block copolymer which comprises a fluorinated block and at least one non-fluorinated block, wherein the fluorinated block has the following structure:



wherein the non-fluorinated block has the following structure:



wherein R<sub>1</sub> is selected from the group consisting of -CH<sub>3</sub>, -CF<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -phenyl, naphthyl, -COOR<sub>3</sub>, and -CONR<sub>3</sub>R<sub>4</sub>;


wherein R<sub>2</sub> is selected from the group consisting of -H, -CH<sub>3</sub>, -CF<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -phenyl, and naphthalenyl; and

wherein R<sub>3</sub> and R<sub>4</sub> are selected from the group consisting of -CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>OH, and -PEG<sub>1</sub>;

wherein n is a positive integer; and

wherein m is a positive integer.

6. (Withdrawn and currently amended) The coating composition of claim 5 wherein the block copolymer has a formula of the following structure:



wherein  $R_1$  is selected from the group consisting of  $-CH_3$ ,  $-CH_2CH_3$ ,  $-CH_2CH_2CH_3$ ,  $-CH_2CH_2CH_2CH_3$ ,  $-CH_2CH_2OH$ , and  $-PEG$ , and

wherein  $R_2$  is selected from the group consisting of  $-H$  or  $-CH_3$ ,  $-CF_3$ ,  $-CH_2CH_3$ ,  $-CH_2CH_2CH_3$ ,  $-CH_2CH_2CH_2CH_3$ ,  $-phenyl$  and  $-naphthyl$ ,


wherein  $n$  is a positive integer, and

wherein  $m$  is a positive integer.

7. (Withdrawn) The coating composition of claim 6 wherein  $R_1$  is selected from the group consisting of  $-CH_3$ ,  $-CH_2CH_3$ ,  $-CH_2CH_2CH_3$ ,  $-CH_2CH_2CH_2CH_3$ ,  $-CH_2CH_2OH$ , or  $-PEG$ , and

wherein  $R_2$  is  $-H$  or  $-CH_3$ .

8. (Withdrawn and currently amended) A polymeric coating composition comprising a block copolymer which comprises a fluorinated block and at least one non-fluorinated block, wherein the fluorinated block has the following structure:



wherein the non-fluorinated block is a polymer selected from the group consisting of polyesters, polyethers, polyanhydrides, polyglycols, poly(alkylene oxides), polyhydroxyalkanoates, polyphosphazenes, polyurethanes, and a combination thereof;

and

wherein n is a positive integer.

9. (Withdrawn) The coating composition of claim 5 further comprising a bioactive agent.

10. (Withdrawn) The coating composition of claim 6 further comprising a bioactive agent.

11. (Withdrawn) The coating composition of claim 7 further comprising a bioactive agent.

12. (Withdrawn) The coating composition of claim 8 further comprising a bioactive agent.

13. (Withdrawn) The coating composition of claim 9 wherein the bioactive agent is selected from the group consisting of tacrolimus, dexamethasone, rapamycin, Everolimus, 40-O-(3-hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-tetrazole-rapamycin.


14. (Withdrawn) The coating composition of claim 10 wherein the bioactive agent is selected from the group consisting of tacrolimus, dexamethasone, rapamycin, Everolimus, 40-O-(3-hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-tetrazole-rapamycin.

15. (Withdrawn) The coating composition of claim 11 wherein the bioactive agent is selected from the group consisting of tacrolimus, dexamethasone, rapamycin, Everolimus, 40-O-(3-hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-tetrazole-rapamycin.


16. (Previously presented) An implantable device comprising a coating which

comprises a block copolymer, the block copolymer comprising a fluorinated block and at least one non-fluorinated block, wherein the fluorinated block is a poly(fluoroalkene).

17. (Currently amended) The implantable device of claim 16, wherein the fluorinated block has the following structure:



wherein the non-fluorinated block has the following structure:



wherein R<sub>1</sub> is selected from the group consisting of -CH<sub>3</sub>, -CF<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -phenyl, naphthyl, -COOR<sub>3</sub>, and -CONR<sub>3</sub>R<sub>4</sub>;


wherein R<sub>2</sub> is selected from the group consisting of -H, -CH<sub>3</sub>, -CF<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -phenyl, and naphthalenyl; and

wherein R<sub>3</sub> and R<sub>4</sub> are selected from the group consisting of -CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>OH, and -PEG<sub>i</sub>;

wherein n is a positive integer; and

wherein m is a positive integer.

18. (Original) The implantable device of claim 17, wherein the block copolymer has a formula of the following structure:



wherein  $R_1$  is selected from the group consisting of  $-\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_2\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_2\text{CH}_2\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_2\text{OH}$ , and  $-\text{PEG}$ , and

wherein  $R_2$  is selected from the group consisting of  $-\text{H}$  or  $-\text{CH}_3$ ,  $-\text{CF}_3$ ,  $-\text{CH}_2\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_2\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_2\text{CH}_2\text{CH}_3$ ,  $-\text{phenyl}$  and  $-\text{naphthyl}$ ,


wherein  $n$  is a positive integer, and

wherein  $m$  is a positive integer.

19. (Previously presented) The implantable device of claim 18 wherein  $R_1$  is selected from the group consisting of  $-\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_2\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_2\text{CH}_2\text{CH}_3$ ,  $-\text{CH}_2\text{CH}_2\text{OH}$ , and  $-\text{PEG}$ , and

wherein  $R_2$  is  $-\text{H}$  or  $-\text{CH}_3$ .

20. (Currently amended) The implantable device of claim 16, wherein the fluorinated block has the following structure:



wherein the non-fluorinated block is a polymer selected from the group consisting of polyesters, polyethers, polyanhydrides, polyglycols, poly(alkylene oxides), polyhydroxyalkanoates, polyphosphazenes, polyurethanes, and a combination thereof;  
and

wherein n is a positive integer.

21. (Original) The implantable device of claim 16, which is a drug-eluting stent, wherein the coating further comprises a bioactive agent.

22. (Original) The implantable device of claim 17, which is a drug-eluting stent, wherein the coating further comprises a bioactive agent.

23. (Original) The implantable device of claim 18, which is a drug-eluting stent, wherein the coating further comprises a bioactive agent.

24. (Original) The implantable device of claim 19, which is a drug-eluting stent, wherein the coating further comprises a bioactive agent.

25. (Original) The implantable device of claim 20, which is a drug-eluting stent, wherein the coating further comprises a bioactive agent.

26. (Previously presented) The implantable device of claim 21, wherein the bioactive agent is selected from the group consisting of tacrolimus, dexamethasone, rapamycin, everolimus, 40-O-(3-hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-tetrazole-rapamycin.

27. (Previously presented) The implantable device of claim 22, wherein the bioactive agent is selected from the group consisting of tacrolimus, dexamethasone, rapamycin, everolimus, 40-O-(3-hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-tetrazole-rapamycin.

28. (Previously presented) The implantable device of claim 23, wherein the bioactive agent is selected from the group consisting of tacrolimus, dexamethasone, rapamycin, everolimus, 40-O-(3-hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-tetrazole-rapamycin.



29. (Previously presented) The implantable device of claim 24, wherein the bioactive agent is selected from the group consisting of tacrolimus, dexamethasone, rapamycin, everolimus, 40-O-(3-hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-tetrazole-rapamycin.

30. (Previously presented) The implantable device of claim 25, wherein the bioactive agent is selected from the group consisting of tacrolimus, dexamethasone, rapamycin, everolimus, 40-O-(3-hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-tetrazole-rapamycin.

31. (Withdrawn) A method of treating restenosis or vulnerable plaque, comprising implanting in a human being in need thereof the implantable device of claim 16.


32. (Withdrawn) A method of treating restenosis or vulnerable plaque, comprising implanting in a human being in need thereof the implantable device of claim 17.

33. (Withdrawn) A method of treating restenosis or vulnerable plaque, comprising implanting in a human being in need thereof the implantable device of claim 26.


34. (Withdrawn) A method of treating restenosis or vulnerable plaque, comprising implanting in a human being in need thereof the implantable device of claim 27.

35. (Withdrawn) A method of treating restenosis or vulnerable plaque, comprising implanting in a human being in need thereof the implantable device of claim 28.

36. (Withdrawn and currently amended) A method of synthesizing a block copolymer comprising a fluorinated block and at least a block of the following structure:



, comprising copolymerizing a monomer having the structure of



in the presence of a di-halo macromer,

wherein R<sub>1</sub> is selected from the group consisting of -CH<sub>3</sub>, -CF<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -phenyl, naphthyl, -COOR<sub>3</sub>, and -CONR<sub>3</sub>R<sub>4</sub>;

wherein R<sub>2</sub> is selected from the group consisting of -H, -CH<sub>3</sub>, -CF<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -phenyl, and naphthalenyl; and

wherein R<sub>3</sub> and R<sub>4</sub> are selected from the group consisting of -CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>3</sub>, -CH<sub>2</sub>CH<sub>2</sub>OH, and -PEG, and;

wherein the di-halo macromer is selected from the group consisting of di-chloro macromer, di-bromo macromer, di-iodo macromer and a combination thereof;

wherein n is a positive integer, and

wherein m is a positive integer.

37. (Withdrawn) The method of claim 36 wherein the di-halo macromer is formed by polymerizing a fluorinated olefin in the presence of a dihalide.

38. (Withdrawn) The method of claim 37 wherein the fluorinated olefin is selected from the group consisting of vinylidene fluoride, hexafluoropropylene, tetrafluoroethylene, and a combination thereof.

39. (Withdrawn) The method of claim 38 wherein the di-halo macromer is prepared by polymerizing a mixture of vinylidene fluoride and 1,1,2,3,3,3-hexafluoropropylene in the presence of 1,2-diiodo-1,1,2,2-difluoroethylene.

40. (Withdrawn and currently amended) The method of claim 39 the di-halo macromer has a structure of

